

2021 Asphalt Mix Designs - Expiration 4-30-2022		
Mix ID.	Mix Design Rice	
		pcf
Martin Marietta		
1223 (5461) - (1.2)SX75(58-28)20%	2.449	152.8
1243 (5462) - (1.2)SX75(64-22)20%	2.450	152.9
1253 (5473) - (1.2)SX75(64-28)20%	2.454	153.1
2223 (5492) - (3.4)SP75(58-28)20%	2.456	153.3
0223 (6967) - (3.8)ST75(58-28)20%	2.433	151.8
0243 (5587) - (3.8)ST75(64-22)20%	2.436	152.0
2243 (5493) - (3.4)S75(64-22)20%	2.461	153.6
Kiewit		
922-CL-21 ST(75)(64-22)	2.401	149.8
920-CL-21 ST (75)(58-28)	2.404	150.0
1922-CL-21 S(75)(64-22)	2.456	153.3
1920-CL-21 S (58-28)	2.454	153.1
1223-CL-21 SX (75)(64-28)	2.439	152.2
1222W-CL-21 SX (75) (64-22) 3 %EVOTHERM	2.435	151.9
1222-CL-21 SX (75) (64-22)	2.437	152.1
1220-CL-21 SX (75) (58-28)	2.435	151.9
1220W-CL-21 SX (75) (58-28) 3 %EVOTHERM	2.437	152.1
Schmidt		
2559-S75R6422-21 Ver. L	2.454	153.1
2581-SX75R5828-21 Ver. L	2.442	152.4
7866 SX75R6428-21 Ver. L	2.443	152.4
2562-S75R6422-21 Ver. L	2.445	152.6
2575-S75R5828-21 Ver. L	2.454	153.1
2562-S75R6422-21 Ver. J	2.446	152.6